

Common Name:

Hindi	Telgu	Bangla	Malyalam	marathi	English	Botanical
रौं जूट	Janapa Nara	Pat	Chanam	ताग	Raw Jute	Corchorus spp.

1.Raw Jute shall be –

- Dried, of minimum reed length of 150 cm, or the effective reed length should not be less than 100 cm
- Free from HUNKA, mud and other foreign materials.

2. Variety.....(to be filled by assayer)**3. Actual Picture of the lot.....(to be uploaded by assayer)****4. Criteria for Range designation**

S.No.	Tradable parameters	Range-1	Range-2	Range-3	Range-4	Range-5
i	Strength (Marks)	Need strength to break the fiber and sharp audible sound at the time of breakage (Excellent 30)	Need less strength to break the fiber and sound will be available at the time of breakage (Good 23)	Need less strength to break the fiber and sound will be available at the time of breakage (Good 23)	Need less strength to break the fiber and feeble sound at the time of breakage(Average 13)	Easily break the fiber and no sound at the time of breakage(Poor 04)
ii	Defects (Marks)	Free from major defects but 10% minor defects may be allowed (25)	90% free from major defects but 20% minor defects may be allowed(17)	80% free from major defects and 30% minor defects may be allowed(09)	80% free from major defects and 30% minor defects may be allowed(09)	70% free from major defects(05)
iii	Root Content (Marks)	< 5% length wise (20)	> 5% -8% length wise(15)	> 8% -10% length wise (08)	> 8% -10% length wise (08)	> 10% length wise(03)
iv	Fineness (Marks)	Very Fine(15)	Very Fine(15)	Fine(10)	Coarse(05)	Coarse(05)
iv	Colour (Marks)	Light creamy to reddish yellow with luster(10)	Light creamy to reddish yellow with luster(10)	Light creamy to reddish yellow with luster(10)	Reddish / brownish with some light grey (05)	Light grey to dark grey(03)
Total Score		Above 80	Above 60	Above 40	Above 20	Less than 20

5. Sampling:

- 5% or minimum one Bunch shall be randomly selected for sampling.
- 1 kg shall be drawn from each selected Bunch and shall be mixed homogenously, called as primary sample.
- 1 kg shall be drawn from primary sample called as Laboratory sample.

6.Note:

- Natural dust may be allowed in Range 3 to 5 with proportionate discount.
- Root content will include hard barky croppy ends.
- Scores on the table may be taken as guidance for determining the discount.
- HUNA: Defects caused by non-removal of dried up base and hard bark from the fibers

Optional parameters are voluntary and may be analyzed as per buyer-seller agreement.